Thermal Management Solutions

Technical Data Sheet



Page 1

GP300 Gap Pad

GP300 is a silicone, thermally conductive material for use at a thermal interface. GP300 is specifically developed as a low thermal resistance gap pad.

- Works well under low pressure
- Good thermal conductivity; 3.0 W/m.K
- Excellent electrical insulation
- · High heat dissipation; low thermal resistance

Approvals	RoHS Compliant (2015/863/EU):	Yes
Typical Properties	Colour:	Sky Blue
	Density @ 20°C (g/ml):	3.0
	Thickness (mm)	0.5 - 1.0
	Hardness (Shore C)	40
	Tensile Strength (MPa):	0.30
	Thermal Conductivity:	3.0 W/m.K
	Temperature Range:	-50°C to +160°C
	Thermal Resistance (°C.in²/W):	0.99
	Elongation (%):	86.5
	Volume Resistivity (Ω·cm):	2.3 x 10 ¹¹
	Dielectric Strength (kV/mm):	7.5
	Dielectric Constant @1MHz:	6.33
	Dielectric Loss:	0.0021
	Compression Ratio (% @ 50psi):	52
	Weight Loss (120°C, 7 days):	0.68%

<u>Description</u>	Order Code	<u>Dimension of Gap Pad</u>	Shelf Life
Gap Pad	GP300S	200 x 200 x 0.5 mm	72 months
Gap Pad	GP300SL	200 x 200 x 1.0 mm	72 months
Gap Pad	GP300SL5DOTS	215 x 111 x 1.0 mm + 5mm Diameter Holes	72 months

Revision 5: June 2019

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way, Ashby de la Zouch, Leicestershire LE65 1JR T +44 (0)1530 419 600 F +44 (0)1530 416 640 BS EN ISO 9001:2008 Certificate No. FM 32082